



材料及工程實驗室-高雄

試 驗 報 告

報告編號：KB-17-07197-1

C-17-17683

頁 數： 1 OF 1

報告日期：106 年 10 月 19 日

委託單位：無機善護宅有限公司

地 址：高雄市前鎮區佛南街 139 號

產品名稱：金鎧甲鋰基強化固化劑

產品型號：SJ-8

產品顏色：透明

供應廠商：無機善護宅有限公司

送驗廠商：無機善護宅有限公司

收件日期：106 年 08 月 09 日

試驗日期：106 年 08 月 09 日~106 年 10 月 19 日

備 註：1.以上資料由顧客提供(收件及試驗日期除外)

2.除非另有說明，此報告結果僅對測試之樣品負責

未經本公司事先書面同意，此報告不可部分複製

試 驗 條 件：

配比	水	I 型水泥	六分石	三分石	粗砂	細砂	藥劑	單位重
kg/m ³	215	307	487	489	402	399	---	2299

試 驗 結 果：

試驗項目	試驗方法	試驗結果	
抗壓強度(kgf/cm ²)	參考 CNS 1232(2002)	參考組(未塗佈)	277
		試驗組(塗佈塗藥劑)	301
磨耗試驗(g)	參考 CNS 3299(2006)	參考組(未塗佈)	0.25
		試驗組(塗佈塗藥劑)	0.20

註：1.試驗組試體表面材料塗抹方式為混凝土試體拆模後，飽和石灰水養護 26 天後氣乾 2 天塗佈藥劑再氣乾 7 天後執行測試。。

2.本試驗之樣品不在 TAF 認可範圍內，故無法出具 TAF 標誌之報告。

3.本試驗報告取代 KB-17-07197 C-17-17683，原試驗報告作廢，報告修改日期 106 年 11 月 09 日。

----- oOo -----

本報告若有提供規範值，該規範值僅供參考，合格之判定以委託單位實際要求為準

報 告 簽 署 人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

SGS Taiwan Ltd.
台灣檢驗科技股份有限公司 | No.61, Kai -Fa Road, Nanzih Export Processing Zone, Kaohsiung, Taiwan / 高雄市楠梓加工出口區開發路 61 號
t (886-7) 301-2121 f (886-7) 301-1165 www.sgs.tw

TWC2384925

2007

Member of SGS Group

cecily_lin



材料及工程實驗室-高雄

試 驗 報 告

報告編號：KB-17-09792

C-17-22853

頁 數： 1 OF 1

報告日期：106 年 11 月 27 日

委託單位：無機善護宅有限公司

地 址：高雄市前鎮區佛南街 139 號

產品名稱：金鎧甲鋰基強化固化劑

產品型號：SJ-8

產品顏色：透明

供應廠商：無機善護宅有限公司

送驗廠商：無機善護宅有限公司

收件日期：106 年 08 月 09 日

試驗日期：106 年 08 月 09 日~106 年 11 月 27 日

備 註：1.以上資料由顧客提供(收件及試驗日期除外)

2.除非另有說明，此報告結果僅對測試之樣品負責

未經本公司事先書面同意，此報告不可部分複製

試驗結果：

試驗項目	試驗方法	試驗結果	
		參考組(未塗佈)	4
磚面耐刮度硬度試驗(度)	參考 CNS 3299(2006)	試驗組(塗佈塗藥劑)	6

註：本試驗之樣品不在 TAF 認可範圍內，故無法出具 TAF 標誌之報告。

----- oOo -----

報告簽署人

本報告若有提供規範值，該規範值僅供參考，合格之判定以委託單位實際要求為準

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

SGS Taiwan Ltd.
台灣檢驗科技股份有限公司 | No.61, Kai -Fa Road, Nanzih Export Processing Zone, Kaohsiung, Taiwan / 高雄市楠梓加工出口區開發路61號
t (886-7) 301-2121 f (886-7) 301-1165 www.sgs.tw

Member of SGS Group

2007
TWC2387861

daisy-tw_huang



材料及工程實驗室-高雄

試驗報告

報告編號：KV-17-07652

頁 數： 1 OF 1

報告日期：106 年 09 月 14 日

委託單位：無機善護宅有限公司

地 址：高雄市前鎮區佛南街 139 號

產品名稱：金鎧甲鋰基強化固化劑

產品型號：SJ-8

產品顏色：透明

供應廠商：無機善護宅有限公司

送驗廠商：無機善護宅有限公司

收件日期：106 年 08 月 08 日

試驗日期：106 年 08 月 08 日~106 年 09 月 14 日

備 註：1.以上資料由顧客提供(收件及試驗日期除外)
 2.除非另有說明，此報告結果僅對測試之樣品負責
 未經本公司事先書面同意，此報告不可部分複製

試驗結果：

試驗項目	試驗方法	試驗結果
耐衝擊性 ($\phi=12.7$ mm, 500 g, 30 cm)	CNS 10757(1995)	無龜裂、剝離現象
耐鹼性(2 % NaOH, 24 h)		鹼浸漬試驗無異常(註 3)

註：1.試驗樣品為單液型。

- 2.依委託單位指定，試片底材為混凝土試體。
 3.目視觀察塗膜確認無膨脹、龜裂、脫離、針孔、軟化、光澤改變、變色，且浸漬過溶液無著色、混濁，則評定為「鹼浸漬試驗無異常」。

----- oOo -----

報告簽署人

本報告若有提供規範值，該規範值僅供參考，合格之判定以委託單位實際要求為準

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

TWC2379833

SGS Taiwan Ltd. | No.61, Kai -Fe Road, Nanzih Export Processing Zone, Kaohsiung, Taiwan / 高雄市楠梓加工出口區開發路61號
 台灣檢驗科技股份有限公司 | (886-7) 301-2121 | (886-7) 301-1165 | www.sgs.tw

2007

Member of SGS Group

frances_kao

國立清華大學原子科學技術發展中心
放射性核種分析實驗室測試報告(2017S121)

地 址 : 新竹市光復路二段 101 號
電 話 : (03) 5715131 轉 35482 : 0972289121
e - m a i l : jhchao@mx.nthu.edu.tw
傳 真 : (03) 5722660

委託單位/統一編號：無機善護宅有限公司/54825803

住 址 : 高雄市前鎮區佛南街 139 號
電 話 : (07)8221158 : 0920177762
傳 真 : (07)8221178
聯 繩 人 : 何仁傑



(106.08.29)

一、採樣地點/日期：台灣檢驗科技股份有限公司委送(KB-17-07197)/2017/08/08

二、試樣種類：建材。

三、採樣程序與前處理：試樣直接裝罐計測。

四、測試程序/儀器：RML-OS-02/純鍺加馬能譜分析系統。

五、計測時間：約60,000秒。

六、分析結果：如下表。

試樣編號	核種活度(貝克/公斤)			比活度 (AI)	備註
	^{40}K	^{232}Th 系	^{238}U 系		
金鎧甲鋰基強化固化劑 型號：SJ-8	< 100	< 10	< 10	< 0.09	符合綠建材 評定原則

註1：鉀(^{40}K)、鈦系(^{232}Th)與鈾系(^{238}U)為天然放射性核種。其中鈦系(^{232}Th)是以其子核種 ^{228}Ac 定量，鈾系(^{238}U) (或 ^{226}Ra)是以其子核種 ^{214}Bi 定量。

註2：比活度(AI)= $^{40}\text{K}/4810 + ^{232}\text{Th}/259 + ^{238}\text{U}/370$ 。AI ≤ 1 則符合綠建材評定原則
(依『財團法人台灣建築中心』100/12/21中建環字第1000005724號函)。

承辦單位簽署：

王君行







